



HEG 205 Rett.
60x120 24"x48"

NEW SIZE



HEG 208 Rett.
60x120 24"x48"

NEW SIZE



HEG 205 Rett.
40x80 16"x32"



HEG 208 Rett.
40x80 16"x32"

	Package 60x120 40x80
Pieces	1 2
Mq.	0,72 0,64
Kg.	33,00 29,50
Boxes	26 24
Mq.	18,72 15,36
Europallet Kg.	878,80 728,00

SHADE VARIATION			
LOW	MODERATE	HIGH	RANDOM

due 2

GRES PORCELLANATO
A TUTTA MASSA
THROUGH-BODY
PORCELAIN TILE
DURCHGEFÄRBTES
FEINSTEINZEUG
LE GRÈS CÉRAME
PLEINE MASSE



SPESSORE

THICKNESS

STAERKE

ÉPAISSEUR

20 mm



RESISTENZA AL GELO

FROST RESISTANCE

FROSTBESTÄNDIGKEIT

RESISTANCE AU GEL

RESISTANT
ISO 10545.12



ASSORBIMENTO
D'ACQUA

WATER ABSORPTION

WASSERAUFNAHME

ABSORPTION D'EAU

~0,1%
ISO 10545.3



CAMPO D'IMPIEGO
CONSIGLIATO

RECOMMENDED USE

ANWENDUNGSBEREICH

PIECE D'EMPLOI
CONSEILLÉE



RESISTENZA CHIMICA

CHEMICAL RESISTANCE

BESTÄNDIGKEIT GEGEN
CHEMIKALIEN

RESISTANCE CHIMIQUE

GA
UNI EN ISO 10545.13
5
UNI EN ISO 10545.14



RESISTENZA ALLA FLESSIONE

BENDING STRENGTH

BIEGEFESTIGKEIT

RÉSISTANCE AU
POINÇONNEMENT STATIQUE

~50 N/mm²
EN 14411 B1a



RESISTENZA ALLO
SCIVOLAMENTO

SLIPPING RESISTANCE

RUTSCHFESTIGKEIT

FACTEUR DE RESISTANCE
ANTIGLISSEMENT

DIN 51130
DIN 51097
ANSI 137.1 (DCOF)
BCRA

ASCIUTTO BAGNATO

DRY WET

TROCKEN NASS

SEC MOUILLE

R 11 -
- **A+B+C**
≥0,42
>0,40 **>0,40**